



The Chemical Company

## CONIDECK 2259<sup>®</sup> (1,0-1,5 mm)

### Polyurethane Based, Car Park Coating System that has the property of Covering Cracks

#### Description of Product

**CONIDECK 2259<sup>®</sup>** is a polyurethane based car park coating system which has high abrasion resistance that is designed for being used in open pavements and slopes under load with a property of covering cracks. Furthermore it is also suitable for intermediate stories under which there are living quarters.

#### Watchpoints

- Avoid application under excessive heat or wind and/or when the ambient and/or substrate temperature is below +10 or above +30°C.
- In applications that will be made under appropriate temperatures, as the application material should have the same temperature as the ambient and substrate temperature, make sure it has been stored for at least 1-2 days at the same temperatures before application.

- In cold conditions the substrate and the material temperatures should be preconditioned to +20 - +25°C by artificial means in order to increase the workability of the product.
- Epoxy and polyurethane based floor coatings should be applied by specialists.
- Reaction and workability times of resin based systems depend on the ambient and substrate temperatures as well as relative humidity. Under lower temperatures, the chemical reaction times are longer and this increases pot life, coating interval and working time. In addition to this, the consumption is increased as the viscosity gets higher. High temperatures ignite stronger chemical reactions and above mentioned time decreases accordingly. For the material to be cured properly, the ambient and substrate temperatures should not fall below specified limits. After application, the material should be protected from direct contact with water for minimum 24 hours. Within this period, contact with water can cause a surface carbonation

#### System Details

Intended Use	Materials	Consumption(kg/m <sup>2</sup> )
Undercoat*	<b>MASTERTOP<sup>®</sup> P 677 Z (CONIPOX<sup>®</sup> 77Z)</b>	0,30 - 0,50
Scatter Sand	Silica Sand 0,1 - 0,3 or 0,3 - 0,8 mm	0,80 - 1,00
Alternative Undercoat (For surface flaws up to 1 mm)	<b>MASTERTOP<sup>®</sup>P 677 Z</b> <i>(It is applied by mixing silica in the ratio 1/0,5 - 1/2 by weight)</i>	0,30 - 0,50
Filler Sand	Silica Sand 0,1 - 0,3 mm or <b>MASTERTOP<sup>®</sup> 1200</b> filler F1a	0,15 - 2,00
Scatter Sand	Silica Sand 0,1 - 0,3 or 0,3 - 0,8 mm	0,80 - 1,00
Final Coat	<b>CONIPUR<sup>®</sup> TC 472 (CONIPUR<sup>®</sup> 272)</b>	0,40 - 0,60

*Alternative undercoats may be used according to infrastructure properties.*



## CONIDECK 2259<sup>®</sup> (1,0-1,5 mm)

and/or tackiness both of which will cause the coating lose its characteristics. In such cases, the overall coating should be removed from the floor and renewed.

- Empty packs should be consolidated and disposed of properly in order to prevent reusing of the packages.
- For detailed information about how to use the products, refer to the Technical Product Information Brochures.

### Attention

The system solutions given above, consumptions and products are given so as to form a basis for calculations considering ideal weather, environment and floor conditions and average employer needs. Changes in the environment and floor conditions and in the needs of the employer can make the consumptions and system solution change. Consequently, the area must be seen by the expert staff of **BASF Yapı Kimyasalları San. A.S.** and/or Expert Implementing Dealers before the system solution and the system solution must be established after the needs of the employer are determined.

### Disclaimer

The technical information and application advice given in this BASF Yapı Kimyasalları San. A.S. publication are based on the present state of our best scientific and practical knowledge. BASF Yapı Kimyasalları San. A.S. is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding place and method of use. This technical form is valid only till the new one is implemented and nullifies the old ones. 01/2008

