



The Chemical Company

MASTERTOP® 1270 CONIFLOOR® H (2,0-3,0 mm)

Epoxy Based, Self Leveling Coating System

Description of Product

MASTERTOP® 1270 is an epoxy based, smooth surfaced, easy to clean, hygienic, self leveling floor coating system used on floors that are exposed to medium - heavy mechanical and chemical effects.

Fields of Application

- Storehouses,
- Production areas,
- Laboratories,
- Chemistry and medicine industries,
- Shopping centers and supermarkets,
- Aircraft hangars,
- Exhibition and fair grounds,
- Garages.

Features and Benefits

- Easy to apply.
- Has high mechanical resistance.
- High resistance against abrasion

- Allows for the traffic of metal wheels over it.
- Surface structure that does not allow the formation of microbes.
- Easily cleaned to create hygienic environments.

Watchpoints

- Avoid application under excessive heat or wind and/or when the ambient and/or substrate temperature is below +10 or above +30°C.
- In applications that will be made under appropriate temperatures, as the application material should have the same temperature as the ambient and substrate temperature, make sure it has been stored for at least 1-2 days at the same temperatures before application.
- In cold conditions the substrate and the material temperatures should be preconditioned to +20 - +25°C by artificial means in order to increase the workability of the product.
- Epoxy and polyurethane based floor coatings should be applied by specialists.

System Details

Intended Use	Materials	Consumption(kg/m ²)
Undercoat	MASTERTOP® P 677 Z (CONIPOX® 77Z)	0,30 - 0,50
Scatter Sand	Silica Sand 0,1 - 0,3 or 0,3 - 0,8 mm	0,80 - 1,00
Alternative Undercoat (For surface flaws up to 1 mm)	MASTERTOP® P 677 Z (CONIPOX® 77Z) <i>(It is applied by mixing silica in the ratio 1/0,5 - 1/2 by weight)</i>	0,30 - 0,50
Filler Sand	Silica Sand 0,1 - 0,3 mm or MASTERTOP® 1200 filler F1a	0,15 - 2,00
Scatter Sand	Silica Sand 0,1 - 0,3 or 0,3 - 0,8 mm	1,00 - 3,00
Pore Sealer	MASTERTOP® BC 370 (CONIPOX® 270)	0,70 - 0,90
Filler Sand	Silica Sand 0,1 - 0,3 mm	0,50 - 0,70
Scatter Sand	Silica Sand 0,1 - 0,3 or 0,3 - 0,8 mm	1,00 - 3,00
Coating	MASTERTOP® BC 370 (CONIPOX® 270)	1,50 - 1,80
Filler Sand	Silica Sand 0,1 - 0,3 mm	1,00 - 1,30
Alternative Final Coat	CONIPUR® 67 N*	0,11 - 0,15

* **CONIPUR® 67** or **MASTERTOP® TC 441P** can be used instead of **CONIPUR® 67 N**. If colored chip application is going to be made on the coating, the chips have to be thrown over **CONIPUR® 67 (N)** and final coat application must be made with **MASTERTOP® 467 C**. Please consult to a **BASF Yapı Kimyasalları San. A.S.** Technical Service for detailed information.



MASTERTOP® 1270 CONIFLOOR® H (2,0-3,0 mm)

- Reaction and workability times of resin based systems depend on the ambient and substrate temperatures as well as relative humidity. Under lower temperatures, the chemical reaction times are longer and this increases pot life, coating interval and working time. In addition to this, the consumption is increased as the viscosity gets higher. High temperatures ignite stronger chemical reactions and above mentioned time decreases accordingly. For the material to be cured properly, the ambient and substrate temperatures should not fall below specified limits. After application, the material should be protected from direct contact with water for minimum 24 hours. Within this period, contact with water can cause a surface carbonation and/or tackiness both of which will cause the coating lose its characteristics. In such cases, the overall coating should be removed from the floor and renewed.
- Empty packs should be consolidated and disposed of properly in order to prevent reusing of the packages.
- For detailed information about how to use the products, refer to the Technical Product Information Brochures.

Attention

The system solutions given above, consumptions and products are given so as to form a basis for calculations considering ideal weather, environment and floor conditions and average employer needs. Changes in the environment and floor conditions and in the needs of the employer can make the consumptions and system solution change. Consequently, the area must be seen by the expert staff of **BASF Yapı Kimyasalları San. A.S.** and/or Expert Implementing Dealers before the system solution and the system solution must be established after the needs of the employer are determined.

Disclaimer

The technical information and application advice given in this BASF Yapı Kimyasalları San. A.S. publication are based on the present state of our best scientific and practical knowledge. BASF Yapı Kimyasalları San. A.S. is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding place and method of use. This technical form is valid only till the new one is implemented and nullifies the old ones. 01/2008

